



Pressure-sensitive adhesives Acrylic Film

1 MIL CLEAR NTC POLYESTER / TS523 @ 1.5 Cwt. / 40#SCK L-3

ITEM #74714

Facestock

This facestock displays high clarity and good UV resistance. The versatile topcoating is compatible with solvent base, water based and UV curable inks and can also perform well when used in silk screen or offset print processes.

Type
Film

Tensile MD
28000 Psi

Tensile CD
34000 Psi

Elong MD
300

Elong CD
110

Properties	Value
------------	-------

Caliper	1.00 Mil
---------	----------

Regulatory Approval

RoHS	Yes	Prop65	Yes	REACH	Yes
TPCH	Yes	CPSIA	Yes	UL	No
FSC	No				

*Please contact your sales representative for details

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Type	Permanent	Composition	Acrylic	Shear	350
Min. Application Temperature	35 F	Min. Service Temperature	-65 F	Max. Application Temperature	200 F

Properties	Value
------------	-------

Stainless Steel	5.6 lbs/linear in.
Glass	2,8lbs/linear in.
Polyethylene	2.9
Corrugated	1.50 lbs./in.
Painted Metal	4.9 lbs/linear in.
Loop Tack	2.70 oz/in ²

Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	Direct Food
Yes	Yes	No
Indirect Food		
Yes		

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34

Tensile CD

22

Tear MD

32

Tear CD

34

Description

Value

Basis Weight

40

Caliper

2.5

Regulatory Approval

RoHS

Yes

TPCH

Yes

Direct Food

No

Prop65

Yes

CPSIA

Yes

REACH

Yes

UL

No

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com