



Pressure-sensitive adhesives Acrylic Film

1.5 MIL PET / TS523 / 40#SCK

ITEM #1574

Description

1.5 MIL PET / TS523 / 40#SCK

Facestock

This item is non-silicone coated.

Type

Film

Tear MD

20 Grams

Elong MD

100

Properties	Value
------------	-------

Caliper	1.50 Mil
---------	----------

Regulatory Approval

FSC

No

*Please contact your sales representative for details

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Type	Composition	Shear
------	-------------	-------

Permanent	Acrylic	350
-----------	---------	-----

Min. Application Temperature	Min. Service Temperature	Max. Application Temperature
------------------------------	--------------------------	------------------------------

35 F	-65 F	200 F
------	-------	-------

Properties	Value
------------	-------

Stainless Steel	5.6 lbs/linear in.
-----------------	--------------------

Glass	2,8lbs/linear in.
-------	-------------------

Polyethylene	2.9	
Corrugated	1.50 lbs./in.	
Painted Metal	4.9 lbs/linear in.	
Loop Tack	2.70 oz/in ²	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		
*Please contact your sales representative for details		

Liner A natural kraft liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type 9019055		
Tensile MD 44	Tensile CD 21	
Tear MD 34	Tear CD 38	
Description Value		
Basis Weight	40	
Caliper	2.5	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.