

Pressure-sensitive adhesives

Acrylic

Paper

17" X 22" NATURAL KRAFT / PERMANENT / 80# SCORE-BACK L-3

ITEM #SC-053

Facestock

This unbleached brown kraft is smudge resistant, has excellent ink receptivity (inks should be designed to avoid excessive absorption) and is designed for high speed converting. It has excellent perforating, punching and fanfolding characteristics.

Type

Paper

Tensile MD

35 Lbs/in

23 Lbs/in

Tear MD

Tear CD

116 Grams

132 Grams

Properties	Value
Basis Weight	50
Caliper	5.50 Mil

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	FSC
Yes	Yes	No

^{*}Please contact your sales representative for details

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Type Permanent	Composition Acrylic
Properties	Value
Glass	2.8 lbs/linear in.
Polyethylene	1.5

Regulatory Approval

RoHSProp65REACHYesYesYes

TPCH CPSIA Direct Food

Yes Yes Yes

Indirect Food

Yes

Liner

This liner is clay-coated bleached kraft designed for roll-to-sheet applications. It is manufactured with scores every 1.25\" apart.

Type

9019084

Tensile MD Tensile CD

36 21

Tear MD Tear CD

61 71

Description	Value
Basis Weight	72
Caliper	4.6

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
ТРСН	CPSIA	UL
Yes	Yes	No

Direct Food

No

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS: Beontag 6206 Wolf Creek

6206 Wolf Creek Pike Trotwood, OH 45426

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details

800-358-4448 orders.us@beontag.com