

Pressure-sensitive adhesives

Acrylic

Film

# 2 MIL CLEAR POLYSTYRENE / TS523 @ 1.5 Cwt. / 44#PK L-4

ITEM #75771

#### **Facestock**

A 2 mil optically clear polystyrene that is oriented, non-formable, non-UV stabilized printing and laminating grade film. This film complies with FDA direct food contact requirements.

## **Type**

Film

Tensile MDTensile CD10800 Psi10800 Psi

### **Elong CD**

100

Properties	Value

Caliper 2.00 Mil

# **Regulatory Approval**

ACH
s
С
)

<sup>\*</sup>Please contact your sales representative for details

## **Adhesive**

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

<b>Type</b> Permanent	<b>Composition</b> Acrylic	Shear 350
<b>Min. Application Temperature</b> 35 F	<b>Min. Service Temperature</b> -65 F	<b>Max. Application Temperature</b> 200 F
Properties	Value	
Stainless Steel	5.6 lbs/linear in.	
Glass	2,8lbs/linear in.	

Polyethylene 2.9

Corrugated 1.50 lbs./in.

Painted Metal 4.9 lbs/linear in.

**Loop Tack** 2.70 oz/in<sup>2</sup>

## **Regulatory Approval**

RoHSProp65REACHYesYesYes

TPCH CPSIA Direct Food

Yes Yes No

#### **Indirect Food**

Yes

#### Liner

A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.

#### **Type**

17745

Tensile MD Tensile CD

35 13

**Tear MD**35

Tear CD

DescriptionValueBasis Weight44Caliper3.2

## **Regulatory Approval**

RoHSProp65REACHYesYesYes
TPCH
CPSIA
Yes
No

## **Direct Food**

No

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com