

2.3 MIL MAJESTIC WHITE BOPP / AP151 @ 1.3 Cwt. / 40#SCK L-3

ITEM #151370

Facestock

A topcoated white polypropylene film with a gloss level of 48%. Product has excellent printability (Thermal Transfer printability with a resin ribbon only), temperature resistance & semi squeezable performance. This face offers balanced orientation for superior die cutting and high stiffness for conversion and automatic dispensing.

Type

Film

Tensile MD

25400 Psi

Tensile CD

22500 Psi

Elong MD

95

Elong CD

115

Properties

Value

Caliper

2.30 Mil

Opacity

80

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

Type

Permanent

Composition

Latex

Shear

80

Min. Application Temperature

35 F

Min. Service Temperature

-65 F

Max. Application Temperature

220 F

Properties

Value

| | |
|------------------------|-------------------------|
| Stainless Steel | 7.3 lbs/linear in. |
| Glass | 5.7 lbs/linear in. |
| Polyethylene | 6.5 |
| Corrugated | 2.50 lbs./in. |
| Painted Metal | 7.0 lbs/linear in. |
| Loop Tack | 5.00 oz/in ² |

Regulatory Approval

| | | |
|-----------------------------|----------------------|--------------------------|
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | Direct Food No |
| Indirect Food Yes | | |

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type
5517342

| | |
|-------------------------|-------------------------|
| Tensile MD 34 | Tensile CD 22 |
| Tear MD 32 | Tear CD 34 |

| Description | Value |
|---------------------|-------|
| Basis Weight | 40 |
| Caliper | 2.5 |

Regulatory Approval

| | | |
|--------------------------|----------------------|---------------------|
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food No | | |

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com