



Pressure-sensitive adhesives

Acrylic

Acrylic

Film

2.6 MIL PEARL WHITE BOPP / AT333 @ 1.7 Cwt / 40#SCK / AT333 / 40#SCK

ITEM #86688

Facestock

A top coated white cavitated BOPP face stock with excellent stability and die cutting capabilities. Printability includes water, solvent, and UV based inks on flexo, gravure, UV letterpress and rotary screen printing systems. It is also thermal transfer printable. This film has excellent stiffness, gloss, and opacity.

Type

Film

Tensile MD

11360 Psi

Tensile CD

22580 Psi

Elong MD

140

Elong CD

47

Properties

Value

Caliper

2.60 Mil

Regulatory Approval

FSC

No

*Please contact your sales representative for details

Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Type

Permanent

Composition

Acrylic

Shear

60

Min. Application Temperature

-20 F

Min. Service Temperature

-65 F

Max. Application Temperature

160 F

Properties

Value

Stainless Steel

5.3 lbs/linear in.

Glass

1,3lbs/linear in.

Polyethylene

2.2

| | |
|----------------------|-------------------------|
| Corrugated | 1.50 lbs./in. |
| Painted Metal | 5.1 lbs/linear in. |
| Loop Tack | 2.40 oz/in ² |

Regulatory Approval

| | | |
|-----------------------------|----------------------|--------------------------|
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | Direct Food No |
| Indirect Food Yes | | |

*Please contact your sales representative for details

Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

| | | |
|--|--|--|
| Type Permanent | Composition Acrylic | Shear 60 |
| Min. Application Temperature -20 F | Min. Service Temperature -65 F | Max. Application Temperature 160 F |

| Properties | Value |
|------------------------|-------------------------|
| Stainless Steel | 4.7 lbs/linear in. |
| Glass | 1,3lbs/linear in. |
| Polyethylene | 2.2 |
| Corrugated | 1.40 lbs./in. |
| Painted Metal | 4.4 lbs/linear in. |
| Loop Tack | 2.20 oz/in ² |

Regulatory Approval

| | | |
|-----------------------------|----------------------|--------------------------|
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | Direct Food No |
| Indirect Food Yes | | |

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34

Tensile CD

22

Tear MD

32

Tear CD

34

Description

Value

Basis Weight

40

Caliper

2.5

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

*Please contact your sales representative for details

Last update: 08/20/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com