

2.6 MIL WHITE TT BOPP / AT333 HCWT / 40#SCK L-3

ITEM #992601

Facestock

A 2.6 Mil matte white polypropylene film that is designed for thermal transfer printability. Features good weather resistance and dimensional stability.

Type
Film

Tensile MD
13800

Tensile CD
26800

Elong MD
170

Elong CD
55

Properties	Value
------------	-------

Caliper	2.6 mil
---------	---------

Regulatory Approval

RoHS	Prop65	REACH
------	--------	-------

Yes	Yes	Yes
-----	-----	-----

TPCH	CPSIA	FSC
------	-------	-----

Yes	Yes	No
-----	-----	----

*Please contact your sales representative for details

Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Type	Composition	Shear
------	-------------	-------

Permanent	Acrylic	60
-----------	---------	----

Min. Application Temperature	Min. Service Temperature	Max. Application Temperature
------------------------------	--------------------------	------------------------------

-20 F	-65 F	160 F
-------	-------	-------

Properties	Value
------------	-------

Stainless Steel	4.9 lbs/linear in.
-----------------	--------------------

Glass	1.3 lbs/linear in.
-------	--------------------

Polyethylene	2.2
--------------	-----

Corrugated	1.50 lbs./in.	
Painted Metal	4.7 lbs/linear in.	
Loop Tack	2.40 oz/in ²	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	Direct Food
Yes	Yes	No
Indirect Food		
Yes		
*Please contact your sales representative for details		

Liner		
Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type		
5517342		
Tensile MD	Tensile CD	
34	22	
Tear MD	Tear CD	
32	34	
DescriptionValue		
Basis Weight	40	
Caliper	2.5	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food		
No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at

BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com