

26" X 20" 2 MIL ULTRA CLEAR BOPP / PERMANENT / 80# ZERO SCORE L-3

ITEM #SC-096

Facestock

A 2 mil clear biaxially oriented polypropylene with exceptional clarity, excellent die-cut performance and great stiffness. Coated gloss surface is print receptive for standard methods.

Type

Film

Tensile MD

20,000 psi

Tensile CD

35,000 psi

Elong MD

180

Elong CD

55%

Properties

Value

Caliper

2.00 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

FSC

No

*Please contact your sales representative for details

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Type

Permanent

Composition

Acrylic

Properties

Value

Glass

2.8 lbs/linear in.

Polyethylene

1.5

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

Direct Food

Yes

Indirect Food

Yes

*Please contact your sales representative for details

Liner

A bleached kraft which has been silicone coated one side to give a controlled release. This paper has high internal strength to withstand all conventional processing operations including die-cutting and butt-cutting.

Type

9019086

Tensile MD

51

Tensile CD

0

Tear MD

0

Tear CD

0

Description**Value****Basis Weight**

72

Caliper

4.6

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)
orders.us@beontag.com