



Pressure-sensitive adhesives

Acrylic

Film

3.0 MIL POLYART / AT333 @ 1.30 Cwt. / 40#SCK L-3

ITEM #66550

FACESTOCK A high performance polyethylene base synthetic paper with a unique computer printable top coating allowing Polyart to be printed with flexo, litho, gravure, letterpress and screen methods. It can also be used with thermal transfer, ion dep, dot matrix and certain ink jets.			
Type Film			
Tensile MD 5800 Psi		Tensile CD 5510 Psi	
Elong MD 130		Elong CD 110	
PROPERTIES		VALUE	
Caliper		3.00 Mil	
Opacity		90	
REGULATORY APPROVAL			
RoHS Yes		Prop65 Yes	REACH Yes
TPCH Yes		CPSIA Yes	FSC No
*Please contact your sales representative for details			

ADHESIVE An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.		
Type Permanent	Composition Acrylic	Shear 60
Min. Application Temperature -20 F	Min. Service Temperature -65 F	Max. Application Temperature 160 F
PROPERTIES	VALUE	
Stainless Steel	4.7 lbs/linear in.	
Glass	1,3lbs/linear in.	
Polyethylene	2.2	
Corrugated	1.40 lbs./in.	
Painted Metal	4.4 lbs/linear in.	

Loop Tack

2.20 oz/in²

REGULATORY APPROVAL

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

Direct Food
No

Indirect Food
Yes

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type
5517342

Tensile MD
34

Tensile CD
22

Tear MD
32

Tear CD
34

DESCRIPTION

VALUE

Basis Weight

40

Caliper

2.5

REGULATORY APPROVAL

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

UL
No

Direct Food
No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com