

# 3.6 MIL POLYART / AT333 @ 1.30 Cwt. / 50#SCK L-3

ITEM #78005

## Facestock

A high performance polyethylene base synthetic paper with a unique computer printable top coating allowing Polyart to be printed with flexo, litho, gravure, letterpress and screen methods. It can also be used with thermal transfer, ion dep and dot matrix.

### Type

Film

### Tensile MD

6670 Psi

### Tensile CD

5510 Psi

### Tear MD

496 Grams

### Tear CD

599 Grams

### Elong MD

120

### Elong CD

110

### Properties

### Value

### Caliper

3.60 Mil

### Opacity

90

## Regulatory Approval

### RoHS

Yes

### Prop65

Yes

### REACH

Yes

### TPCH

Yes

### CPSIA

Yes

### FSC

No

\*Please contact your sales representative for details

## Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

### Type

Permanent

### Composition

Acrylic

### Shear

60

### Min. Application Temperature

-20 F

### Min. Service Temperature

-65 F

### Max. Application Temperature

160 F

### Properties

### Value

Stainless Steel	4.7 lbs/linear in.	
Glass	1,3lbs/linear in.	
Polyethylene	2.2	
Corrugated	1.40 lbs./in.	
Painted Metal	4.4 lbs/linear in.	
Loop Tack	2.20 oz/in²	
<hr/>		
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	Direct Food
Yes	Yes	No
Indirect Food		
Yes		
*Please contact your sales representative for details		

<b>Liner</b> Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
<b>Type</b> 5517353		
<b>Tensile MD</b> 40	<b>Tensile CD</b> 24	
<b>Tear MD</b> 44	<b>Tear CD</b> 48	
<b>Description</b>	<b>Value</b>	
<b>Basis Weight</b>	50	
<b>Caliper</b>	3.2	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		
*Please contact your sales representative for details		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)