

3.6 MIL POLYART TS523 65# C2S

ITEM #78061

Facestock

A high performance polyethylene base synthetic paper with a unique computer printable top coating allowing Polyart to be printed with flexo, litho, gravure, letterpress and screen methods. It can also be used with thermal transfer, ion dep and dot matrix.

Type

Film

Tensile MD

6670 Psi

Tensile CD

5510 Psi

Tear MD

496 Grams

Tear CD

599 Grams

Elong MD

120

Elong CD

110

Properties

Value

Caliper

3.60 Mil

Opacity

90

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Type

Permanent

Composition

Acrylic

Shear

350

Min. Application Temperature

35 F

Min. Service Temperature

-65 F

Max. Application Temperature

200 F

Properties

Value

Stainless Steel	5.6 lbs/linear in.
Glass	2,8lbs/linear in.
Polyethylene	2.9
Corrugated	1.50 lbs./in.
Painted Metal	4.9 lbs/linear in.
Loop Tack	2.70 oz/in²

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	Direct Food
Yes	Yes	No
Indirect Food		
Yes		

*Please contact your sales representative for details

Liner A fully bleached kraft liner which has been silicone coated one side to give a controlled release. This paper has high internal strength top withstand all conventional processing operations including die-cutting, perforating, fanfolding and refolding processes.		
Type 47365		
Tensile MD 33	Tensile CD 18	
Tear MD 51	Tear CD 53	
Description	Value	
Basis Weight	65	
Caliper	3.8	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Liner A fully bleached kraft liner which has been silicone coated one side to give a controlled release. This paper has high internal strength top withstand all conventional processing operations including die-cutting, perforating, fanfolding and refolding processes.

Type 47365		
Tensile MD 33 Lbs/In	Tensile CD 18 Lbs/In	
Tear MD 51 Grams	Tear CD 53 Grams	
Description	Value	
Basis Weight	65 Lbs/Rm	
Caliper	3.8 Mil	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com