

Pressure-sensitive adhesives

Acrylic

Film

3.7 MIL SMUDGE KIMDURA / AT333 @ 1.30 Cwt. / 50#SCK L-3

ITEM #8992

Facestock

A 3.7 mil white Smudge Kimdura which is a biaxially oriented three ply polypropylene which combines extraordinary edge tear resistance with a smooth, uniform surface that provides brilliant imagery, superior print quality and smudge resistance.

Type

Film

Tensile MD
24 Lbs/in
18 Lbs/in

Tear MD
26 Grams
15 Grams

Value

Caliper 3.70 Mil

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	FSC
Yes	Yes	No

^{*}Please contact your sales representative for details

Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Type Permanent	Composition Acrylic	Shear 60
Min. Application Temperature -20 F	Min. Service Temperature -65 F	Max. Application Temperature 160 F
Properties	Value	
Stainless Steel	4.7 lbs/linear in.	

Glass 1,3lbs/linear in.

Polyethylene 2.2

Corrugated 1.40 lbs./in.

Painted Metal 4.4 lbs/linear in.

Loop Tack 2.20 oz/in²

Regulatory Approval

RoHSProp65REACHYesYesYes

TPCH CPSIA Direct Food

Yes Yes No

Indirect Food

Yes

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517353

Tensile MD Tensile CD

40 24

Tear MD Tear CD 48

DescriptionValueBasis Weight50Caliper3.2

Regulatory Approval

RoHSProp65REACHYesYesYes
TPCH
CPSIA
Yes
No

Direct Food

No

Last update: 05/01/2024

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com