

# 4 MIL FLEXIBLE TC VINYL / AP151 @ 1.3 Cwt. / 65#FBK L-3

ITEM #978093

## Facestock

A 4 mil flexible white vinyl with polymeric plasticizers, formulated to provide optimum performance with pressure sensitive adhesives. The top-coating provides outstanding adhesion to various printing inks.

### Type

Film

### Tensile MD

3900 lb/in

### Tensile CD

3800 lb/in

### Tear MD

100 Grams

### Tear CD

100 Grams

### Properties

### Value

### Caliper

4.0

## Regulatory Approval

### RoHS

Yes

### Prop65

Yes

### REACH

Yes

### TPCH

Yes

### CPSIA

Yes

### FSC

No

\*Please contact your sales representative for details

## Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

### Type

Permanent

### Composition

Latex

### Shear

80

### Min. Application Temperature

35 F

### Min. Service Temperature

-65 F

### Max. Application Temperature

220 F

### Properties

### Value

### Stainless Steel

7.3 lbs/linear in.

### Glass

5.7 lbs/linear in.

<b>Polyethylene</b>	6.5
<b>Corrugated</b>	2.50 lbs./in.
<b>Painted Metal</b>	7.0 lbs/linear in.
<b>Loop Tack</b>	5.00 oz/in <sup>2</sup>

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>Direct Food</b> No
<b>Indirect Food</b> Yes		

\*Please contact your sales representative for details

### Liner

A fully bleached kraft liner which has been silicone coated one side to give a controlled release. This paper has high internal strength to withstand all conventional processing operations including die-cutting, perforating, fanfolding and refolding processes.

#### Type

17365

<b>Tensile MD</b> 33	<b>Tensile CD</b> 18
<b>Tear MD</b> 51	<b>Tear CD</b> 53

Description	Value
<b>Basis Weight</b>	65
<b>Caliper</b>	3.8

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)