



Pressure-sensitive adhesives Acrylic Paper

50# BRIGHT WHITE EDP / AT333 @ 1.30 Cwt. / 40#SCK L-3

ITEM #4408238

Facestock

This is a high brightness, surface-sized free sheet. Its smoothness and optical properties are designed to yield clean, crisp printed images. Its physical properties provide the dimensional stability and strength required in the pressure sensitive label converting process.

Type

Paper

Tensile MD

30 Lbs/in

Tensile CD

15 Lbs/in

Tear MD

40 Grams

Tear CD

50 Grams

Properties	Value
Basis Weight	50lbs/3300 sq ft
Caliper	3.50 Mil
Opacity	90
Brightness	92

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	FSC
Yes	Yes	No

*Please contact your sales representative for details

Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Type	Composition	Shear
Permanent	Acrylic	60
Min. Application Temperature	Min. Service Temperature	Max. Application Temperature
-20 F	-65 F	160 F

Properties	Value
Stainless Steel	4.7 lbs/linear in.
Glass	1,3lbs/linear in.
Polyethylene	2.2
Corrugated	1.40 lbs./in.
Painted Metal	4.4 lbs/linear in.
Loop Tack	2.20 oz/in²

Regulatory Approval

RoHS

Yes

TPCH

Yes

Indirect Food

Yes

Prop65

Yes

CPSIA

Yes

REACH

Yes

Direct Food

No

*Please contact your sales representative for details

<div>Liner</div> <div>Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.</div>		
Type	5517342	
Tensile MD	34	Tensile CD 22
Tear MD	32	Tear CD 34

Description	Value
Basis Weight	40
Caliper	2.5

Regulatory Approval

RoHS

Yes

TPCH

Yes

Direct Food

No

Prop65

Yes

CPSIA

Yes

REACH

Yes

UL

No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com