

50# RADIANT WHITE LASER / TR440 @ 1.0 Cwt. / 3.4 MIL LAYFLAT L-3

ITEM #559583

Facestock	
<div><div>Type</div><div>Paper</div></div>	
<div><div>Tensile MD</div><div>34 Lbs/in</div></div>	<div><div>Tensile CD</div><div>22 Lbs/in</div></div>
<div><div>Tear MD</div><div>50 Grams</div></div>	<div><div>Tear CD</div><div>56 Grams</div></div>
Properties	Value
Basis Weight	56lbs/3300 sq ft
Caliper	4.00 Mil
Opacity	89
Brightness	94
Regulatory Approval	
<div><div>FSC</div><div>No</div></div>	
*Please contact your sales representative for details	

Adhesive		
<div>A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity &amp; minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.</div>		
<div><div>Type</div><div>Removable</div></div>	<div><div>Composition</div><div>Acrylic</div></div>	<div><div>Shear</div><div>110</div></div>
<div><div>Min. Application Temperature</div><div>40 F</div></div>	<div><div>Min. Service Temperature</div><div>-65 F</div></div>	<div><div>Max. Application Temperature</div><div>150 F</div></div>
Properties	Value	
Stainless Steel	4.7 lbs/linear in.	

<b>Glass</b>	3lbs/linear in.	
<b>Polyethylene</b>	1.4	
<b>Corrugated</b>	1.20 lbs./in.	
<b>Painted Metal</b>	4.2 lbs/linear in.	
<b>Loop Tack</b>	1.70 oz/in <sup>2</sup>	
<hr/>		
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>Direct Food</b> No
<b>Indirect Food</b> Yes		
*Please contact your sales representative for details		

Liner

A bleached kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand die-cutting, marginal punching, perforating, fanfolding and refolding process while providing excellent dimensional stability.

Tensile MD

35

Tensile CD

15

Tear MD

50

Tear CD

75

Description

Value

Basis Weight

0

Caliper

3,4

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:  
Beontag  
6206 Wolf Creek Pike  
Trotwood, OH 45426  
[800-358-4448](tel:800-358-4448)  
[orders.us@beontag.com](mailto:orders.us@beontag.com)