

Pressure-sensitive adhesives

Acrylic

Paper

50# RADIANT WHITE LASER / TS523 @ 1.5 Cwt. / 2.5 MIL LAYFLAT L-3

ITEM #69586

Facestock

Type

Paper

Tensile MD

34 Lbs/in

Tensile CD

22 Lbs/in

Tear MD

50 Grams

Tear CD

56 Grams

Properties

Value

Basis Weight

56lbs/3300 sq ft

Caliper

4.00 Mil

Opacity

89

Brightness

94

Regulatory Approval

FSC

No

*Please contact your sales representative for details

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Type

Permanent

Composition

Acrylic

Shear

350

Min. Application Temperature

35 F

Min. Service Temperature

-65 F

Max. Application Temperature

200 F

Properties

Value

Stainless Steel

5.6 lbs/linear in.

| | |
|----------------------|-------------------------|
| Glass | 2,8lbs/linear in. |
| Polyethylene | 2.9 |
| Corrugated | 1.50 lbs./in. |
| Painted Metal | 4.9 lbs/linear in. |
| Loop Tack | 2.70 oz/in ² |

Regulatory Approval

| | | |
|-----------------------------|----------------------|--------------------------|
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | Direct Food No |
| Indirect Food Yes | | |

*Please contact your sales representative for details

Liner

A bleached kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand die-cutting and has excellent layflat characteristics while providing outstanding dimensional stability.

Type
901967

| | |
|-------------------------|-------------------------|
| Tensile MD 24 | Tensile CD 10 |
| Tear MD 28 | Tear CD 32 |

| Description | Value |
|---------------------|-------|
| Basis Weight | 40 |
| Caliper | 2.5 |

Regulatory Approval

| | | |
|--------------------------|----------------------|---------------------|
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | UL No |
| Direct Food No | | |

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com