

Pressure-sensitive adhesives

Latex

Latex

Paper

#55 HIBRIGHT SEMIGLOSS / TP120 @ 1.3 Cwt./ 40#SCK L-3

ITEM #9772

Facestock

A premium semigloss calendar coated one side stock with excellent ink receptivity and print characteristics. This stock offers an 88% brightness has an 87% opacity and a 70% gloss rating.

Type

Paper

Tensile MD

35 Lbs/in

Tensile CD

16 Lbs/in

Tear MD

35 Grams

Tear CD

38 Grams

Properties

Value

Basis Weight

55

Caliper

2.80 Mil

Opacity

87

Brightness

88

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive

A general purpose permanent rubber based adhesive showing high initial tack with high shear and high ultimate adhesion. It has fair plasticizer, UV and solvent resistance. TP120 is not recommended for water immersion. This adhesive has good adhesion to most substrates.

Type

Perm

Composition

Latex

Properties

Value

Glass	5.7 lbs/linear in.
Polyethylene	5.1

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No	Indirect Food Yes	FDA 21 CFR 175.105, BfR XIV No

*Please contact your sales representative for details

Adhesive

A general purpose permanent rubber based adhesive showing high initial tack with high shear and high ultimate adhesion. It has fair plasticizer, UV and solvent resistance. TP120 is not recommended for water immersion. This adhesive has good adhesion to most substrates.

Type Permanent	Composition Latex	Shear 0
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 200 F

Properties	Value
Stainless Steel	5.1 lbs/linear in.
Glass	2,5lbs/linear in.
Polyethylene	5.1
Painted Metal	4.8 lbs/linear in.

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34

Tensile CD

22

Tear MD

32

Tear CD

34

Description

Value

Basis Weight

40

Caliper

2.5

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com