

60# BRIGHT WHITE EDP / AP151 @ 1.3 Cwt. / 80#FBK L-3

ITEM #151919

Facestock

This white uncoated litho was designed with smudge resistance for high speed converting while still having excellent perforating, punching & fanfolding characteristics. This stock also offers an 88% in brightness & an 84% opacity.

Type
Paper

Regulatory Approval

Prop65	FSC
Yes	No

*Please contact your sales representative for details

Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

Type	Composition	Shear
Permanent	Latex	80
Min. Application Temperature	Min. Service Temperature	Max. Application Temperature
35 F	-65 F	220 F

Properties	Value
Stainless Steel	7.3 lbs/linear in.
Glass	5.7 lbs/linear in.
Polyethylene	6.5
Corrugated	2.50 lbs./in.
Painted Metal	7.0 lbs/linear in.
Loop Tack	5.00 oz/in²

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes

TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		
*Please contact your sales representative for details		

Liner A fully bleached kraft liner (FBK) which has been silicone coated one side to give a controlled release. It is designed to withstand all die-cutting, marginal punching, perforating, fanfolding and refolding processes. It is an excellent lay-flat liner.		
Tensile MD 40	Tensile CD 21	
Tear MD 76	Tear CD 84	
Description	Value	
Basis Weight	0	
Caliper	4,5	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com