



Pressure-sensitive adhesives

Acrylic

Paper

# 60# CLASSIC NATURAL WHITE FELT WS / TS585WS @ 1.6 Cwt. / 44#PK L-4

ITEM #78879

## Facestock

This 60# text weight natural white felt paper features great ink holdout and glue adhesion.

### Type

Paper

### Tensile MD

8 Lbs/in

### Tensile CD

6 Lbs/in

### Properties

### Value

### Basis Weight

60 # Rm 25 x 38

### Caliper

4.40 Mil

### Opacity

90

### Brightness

79

## Regulatory Approval

### RoHS

Yes

### Prop65

Yes

### REACH

Yes

### TPCH

Yes

### CPSIA

Yes

### FSC

No

\*Please contact your sales representative for details

## Adhesive

A specialty adhesive designed to adhere to slightly wet surfaces with good ultimate adhesion when applied at temperatures as low as -20 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for hard to label substrates.

### Type

Permanent

### Composition

Acrylic

### Shear

65

### Min. Application Temperature

-20 F

### Min. Service Temperature

-65 F

### Max. Application Temperature

140 F

### Properties

### Value

### Stainless Steel

4.8 lbs/linear in.

<b>Glass</b>	3,2lbs/linear in.
<b>Polyethylene</b>	6,5lbs/linear in.
<b>Corrugated</b>	1.45 lbs./in.
<b>Painted Metal</b>	4.4 lbs/linear in.
<b>Loop Tack</b>	2.70 oz/in <sup>2</sup>

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>Direct Food</b> No
<b>Indirect Food</b> Yes		

\*Please contact your sales representative for details

### Liner

A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.

**Type**  
17745

<b>Tensile MD</b> 35	<b>Tensile CD</b> 13
<b>Tear MD</b> 35	<b>Tear CD</b> 50

Description	Value
<b>Basis Weight</b>	44
<b>Caliper</b>	3.2

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		

\*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)