

60# ULTRA WHITE SemiGloss / TS523 @ 1.5 Cwt. / 40#SCK L-3

ITEM #79175

Facestock

A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 90% Brightness and an 88% opacity.

Type

Paper

Tensile MD

35 Lbs/in

Tensile CD

19 Lbs/in

Tear MD

47 Grams

Tear CD

46 Grams

Properties

Value

Basis Weight

60 # Rm 25 x 38

Caliper

3.20 Mil

Opacity

88

Brightness

90

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

\*Please contact your sales representative for details

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Type

Permanent

Composition

Acrylic

Shear

350

Min. Application Temperature

35 F

Min. Service Temperature

-65 F

Max. Application Temperature

200 F

Properties	Value	
Stainless Steel	5.6 lbs/linear in.	
Glass	2,8lbs/linear in.	
Polyethylene	2.9	
Corrugated	1.50 lbs./in.	
Painted Metal	4.9 lbs/linear in.	
Loop Tack	2.70 oz/in <sup>2</sup>	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	Direct Food
Yes	Yes	No
Indirect Food		
Yes		
*Please contact your sales representative for details		

Liner		
Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type		
5517342		
Tensile MD	Tensile CD	
34	22	
Tear MD	Tear CD	
32	34	
Description	Value	
Basis Weight	40	
Caliper	2.5	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food		
No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)