

Pressure-sensitive adhesives

Acrylic

Paper

8 PT TAG / IP400 @ 1.7 Cwt. / 40#SCK L-10

ITEM #72354

Facestock

A coated 1 side tag stock with exceptionally high internal strength. It also offers high stiffness to withstand most conventional processing conditions such as die-cutting, perforating, fan-folding, and refolding operations

Type

Paper

Tensile MD

70

Tensile CD

32

Tear MD

130

Tear CD

130

Properties

Value

Basis Weight

100

Caliper

8 mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

FSC

No

*Please contact your sales representative for details

Adhesive

A specialty adhesive designed to adhere to glass wine bottles with good ultimate adhesion when applied at temperatures as low as +35 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for wet strength wine label facestocks when submersed in ice buckets.

Type

Permanent

Composition

Acrylic

Shear

80

Min. Application Temperature

35 F

Min. Service Temperature

-65 F

Max. Application Temperature

200 F

Properties

Value

Stainless Steel	5.5 lbs/linear in.
Glass	3,2lbs/linear in.
Polyethylene	2
Corrugated	1.45 lbs./in.
Painted Metal	3.0 lbs/linear in.
Loop Tack	5.00 oz/in ²

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type
17142

Tensile MD 34	Tensile CD 22
Tear MD 32	Tear CD 34

Description	Value
Basis Weight	40
Caliper	2.5

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com