

# 8.5" X 11" BRIGHT WHITE GLOSS / PERMANENT / 80# SCOREBACK L-3



ITEM #SC-004

## Facestock

A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 90% Brightness and an 88% opacity.

### Type

Paper

### Tensile MD

35 Lbs/in

### Tensile CD

19 Lbs/in

### Tear MD

47 Grams

### Tear CD

46 Grams

### Properties

### Value

### Caliper

3.20 Mil

### Opacity

88

### Brightness

90

## Regulatory Approval

### RoHS

Yes

### Prop65

Yes

### REACH

Yes

### TPCH

Yes

### CPSIA

Yes

### FSC

Yes

\*Please contact your sales representative for details

## Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

### Type

Permanent

### Composition

Acrylic

### Shear

300

### Application Temperature

35 F

### Min. Application Temperature

-65 F

### Max. Application Temperature

180 F

### Properties

### Value

<b>Stainless Steel</b>	5.2 lbs/linear in.
<b>Glass</b>	2.8
<b>Polyethylene</b>	2.9
<b>Corrugated</b>	1.40 lbs./in.
<b>Painted Metal</b>	5.2 lbs/linear in.
<b>Loop Tack</b>	2.20 lbs./in <sup>2</sup>

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> Yes	<b>Indirect Food</b> Yes	

\*Please contact your sales representative for details

### Liner

This liner is clay-coated bleached kraft designed for roll-to-sheet applications. It is manufactured with scores every 1.25" apart.

**Type**  
9019084

**Tensile MD**  
36 Lbs/In

**Tensile CD**  
21 Lbs/In

**Tear MD**  
61 Grams

**Tear CD**  
71 Grams

Description	Value
<b>Basis Weight</b>	72 Lbs/Rm
<b>Caliper</b>	4.6 Mil

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		

\*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)