

Bright Silver Laminated Foil / TR440 @ 1.0 Cwt. / 50#SCK L-3

ITEM #1204

Facestock

An acrylic topcoating comes standard on this product designed to accept water-based and solvent inks.

Type

Paper

Tensile MD

30 Lbs/in

Tensile CD

18 Lbs/in

Tear MD

41 Grams

Tear CD

49 Grams

Properties

Value

Basis Weight

64

Caliper

3.60 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

| | | |
|---|--|--|
| Adhesive A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces. | | |
| Type Removable | Composition Acrylic | Shear 110 |
| Min. Application Temperature 40 F | Min. Service Temperature -65 F | Max. Application Temperature 150 F |
| | | |
| Properties | Value | |
| Stainless Steel | 4.7 lbs/linear in. | |

| | | |
|---|-------------------------|--------------------------|
| Glass | 3lbs/linear in. | |
| Polyethylene | 1.4 | |
| Corrugated | 1.20 lbs./in. | |
| Painted Metal | 4.2 lbs/linear in. | |
| Loop Tack | 1.70 oz/in ² | |
| <hr/> | | |
| Regulatory Approval | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | Direct Food No |
| Indirect Food Yes | | |
| *Please contact your sales representative for details | | |

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517353

Tensile MD

40

Tensile CD

24

Tear MD

44

Tear CD

48

Description

Value

Basis Weight

50

Caliper

3.2

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com