

BRIGHT WHITE EDP AP151 40#SCK L-3

ITEM #4151017

Facestock

This is a high brightness, surface-sized free sheet. Its smoothness and optical properties are designed to yield clean, crisp printed images. Its physical properties provide the dimensional stability and strength required in the pressure sensitive label converting process.

Type

Paper

Tensile MD

30 Lbs/in

Tensile CD

15 Lbs/in

Tear MD

40 Grams

Tear CD

50 Grams

Properties

Value

Basis Weight

50lbs/3300 sq ft

Caliper

3.50 Mil

Opacity

90

Brightness

92

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

Type

Permanent

Composition

Latex

Shear

80

Min. Application Temperature

35 F

Min. Service Temperature

-65 F

Max. Application Temperature

220 F

Properties	Value	
Stainless Steel	7.3 lbs/linear in.	
Glass	5.7 lbs/linear in.	
Polyethylene	6.5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	
Loop Tack	5.00 oz/in ²	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	Direct Food
Yes	Yes	No
Indirect Food		
Yes		
*Please contact your sales representative for details		

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34

Tensile CD

22

Tear MD

32

Tear CD

34

Description

Value

Basis Weight

40

Caliper

2.5

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

*Please contact your sales representative for details

Last update: 08/19/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com