

Pressure-sensitive adhesives

Acrylic

Paper

# BRIGHT WHITE EDP / TP160 @ 1.3 Cwt. / 50#SCK L-3

ITEM #9009229

## Facestock

A white uncoated litho designed with smudge resistance for high speed converting while having excellent perforating, punching and fanfolding characteristics. This stock also offers 88% in brightness and 83% opacity.

### Type

Paper

### Tensile MD

40 Lbs/in

### Tensile CD

20 Lbs/in

### Tear MD

45 Grams

### Tear CD

50 Grams

### Properties

### Value

### Basis Weight

50 # Rm 25 x 38

### Caliper

3.50 Mil

### Opacity

85

### Brightness

88

## Regulatory Approval

### FSC

No

\*Please contact your sales representative for details

## Adhesive

An improved general purpose acrylic adhesive showing good initial tack, shear, and high ultimate adhesion. It has a good plasticizer, UV and solvent resistance, as well as compostability. This adhesive also displays excellent die-cutting and stripping traits & has excellent adhesion to many different substrates, with an application temperature of +25 °F.

### Type

Permanent

### Composition

Acrylic

### Shear

79

### Min. Application Temperature

25 F

### Min. Service Temperature

-65 F

### Max. Application Temperature

200 F

### Properties

### Value

### Stainless Steel

6.8 lbs/linear in.

<b>Glass</b>	0lbs/linear in.
<b>Polyethylene</b>	6.5
<b>Corrugated</b>	1.20 lbs./in.
<b>Painted Metal</b>	6.4 lbs/linear in.
<b>Loop Tack</b>	2.90 oz/in <sup>2</sup>

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>Direct Food</b> No
<b>Indirect Food</b> Yes		

\*Please contact your sales representative for details

### Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

**Type**  
5517353

<b>Tensile MD</b> 40	<b>Tensile CD</b> 24
<b>Tear MD</b> 44	<b>Tear CD</b> 48

Description	Value
<b>Basis Weight</b>	50
<b>Caliper</b>	3.2

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		

\*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)