

BRIGHT WHITE EDP / TP160 @ 1.3 Cwt. / 50#SCK L-3

ITEM #9009229

Facestock A white uncoated litho designed with smudge resistance for high speed converting while having excellent perforating, punching and fanfolding characteristics. This stock also offers 88% in brightness and 83% opacity.	
Type Paper	
Tensile MD 40 Lbs/in	Tensile CD 20 Lbs/in
Tear MD 45 Grams	Tear CD 50 Grams
Properties	Value
Basis Weight	50 # Rm 25 x 38
Caliper	3.50 Mil
Opacity	85
Brightness	88
Regulatory Approval	
FSC No	
*Please contact your sales representative for details	

Adhesive An improved general purpose acrylic adhesive showing good initial tack, shear, and high ultimate adhesion. It has a good plasticizer, UV and solvent resistance, as well as compostability. This adhesive also displays excellent die-cutting and stripping traits & has excellent adhesion to many different substrates, with an application temperature of +25 °F.		
Type Permanent	Composition Acrylic	Shear 79
Min. Application Temperature 25 F	Min. Service Temperature -65 F	Max. Application Temperature 200 F
Properties	Value	
Stainless Steel	6.8 lbs/linear in.	

Glass	0lbs/linear in.	
Polyethylene	6.5	
Corrugated	1.20 lbs./in.	
Painted Metal	6.4 lbs/linear in.	
Loop Tack	2.90 oz/in ²	
<hr/>		
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		
*Please contact your sales representative for details		

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type		
5517353		
Tensile MD	Tensile CD	
40	24	
Tear MD	Tear CD	
44	48	

Description	Value	
Basis Weight	50	
Caliper	3.2	

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food		
No		

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com