

Pressure-sensitive adhesives

Acrylic

Paper

BRIGHT WHITE EDP / TS523 @ 1.5 Cwt. / 1.5 MIL PET L-3

ITEM #4489645

Facestock

A white uncoated litho designed with smudge resistance for high speed converting while having excellent perforating, punching and fanfolding characteristics. This stock also offers 88% in brightness and 83% opacity.

Type

Paper

Tensile MD

40 Lbs/in

Tensile CD

20 Lbs/in

Tear MD

45 Grams

Tear CD

50 Grams

Properties

Value

Basis Weight

50 # Rm 25 x 38

Caliper

3.50 Mil

Opacity

85

Brightness

88

Regulatory Approval

FSC

No

*Please contact your sales representative for details

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Type

Permanent

Composition

Acrylic

Shear

350

Min. Application Temperature

35 F

Min. Service Temperature

-65 F

Max. Application Temperature

200 F

Properties

Value

Stainless Steel	5.6 lbs/linear in.
Glass	2,8lbs/linear in.
Polyethylene	2.9
Corrugated	1.50 lbs./in.
Painted Metal	4.9 lbs/linear in.
Loop Tack	2.70 oz/in ²

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

Liner

A 1.5 mil polyester liner which has been silicone coated one side to give a controlled release. It has extremely high internal strength for ease in manufacturing, converting and end usage, making it an outstanding liner for high speed, automatic applications.

Type
619827

Tensile MD 32000	Tensile CD 0
----------------------------	------------------------

Tear MD 0	Tear CD 0
---------------------	---------------------

Description	Value
-------------	-------

Caliper	1.5
----------------	-----

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com