

Pressure-sensitive adhesives

Acrylic

Paper

DULL SILVER LAMINATED FOIL / TS523 @ 1.5 Cwt. / 40#SCK L-3

ITEM #894

Facestock

A 60# acrylic topcoated foil paper that accepts water base and solvent base inks and can be embossed.

Type

Paper

Tensile MD

36 Lbs/in

23 Lbs/in

Tear MD

Tear CD

50 Grams

51 Grams

| Properties | Value |
|------------|-------|
|------------|-------|

Basis Weight $60 \# \text{Rm } 25 \times 38$

Caliper 3.60 Mil

Regulatory Approval

| RoHS | Prop65 | REACH |
|------|--------|------------|
| Yes | Yes | Yes |
| TDOU | 00014 | 500 |
| TPCH | CPSIA | FSC |
| Yes | Yes | No |

^{*}Please contact your sales representative for details

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

| Type Permanent | Composition Acrylic | Shear 350 |
|--|--|---|
| Min. Application Temperature 35 F | Min. Service Temperature -65 F | Max. Application Temperature 200 F |
| Properties | Value | |
| Stainless Steel | 5.6 lbs/linear in. | |

Glass 2,8lbs/linear in.

Polyethylene 2.9

Corrugated 1.50 lbs./in.

Painted Metal 4.9 lbs/linear in.

Loop Tack 2.70 oz/in²

Regulatory Approval

RoHSProp65REACHYesYesYes

TPCH CPSIA Direct Food

Yes Yes No

Indirect Food

Yes

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD Tensile CD

34 22

Tear MD Tear CD 32 34

DescriptionValueBasis Weight40Caliper2.5

Regulatory Approval

RoHSProp65REACHYesYesYes
TPCH
CPSIA
Yes
No

Direct Food

No

Last update: 05/01/2024

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com