

Pressure-sensitive adhesives

Latex

Paper

# ORANGE FLUORESCENT / AP151 @ 1.3 Cwt. / 40#SCK L-3

ITEM #151024

#### **Facestock**

A premium coated one side face stock in a bright fluorescent color with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting.

# Туре

Paper

Tensile MD
26 Lbs/in
14 Lbs/in

Tear MD
45 Grams
53 Grams

Properties	Value
Basis Weight	54 # Rm 25 x 38

Caliper 3.80 Mil

# **Regulatory Approval**

RoHSProp65REACHYesYesYes
TPCH
CPSIA
FSC
Yes
No

## **Adhesive**

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

<b>Type</b> Permanent	<b>Composition</b> Latex	<b>Shear</b> 80
<b>Min. Application Temperature</b> 35 F	<b>Min. Service Temperature</b> -65 F	<b>Max. Application Temperature</b> 220 F
Properties	Value	
Stainless Steel	7.3 lbs/linear in.	

<sup>\*</sup>Please contact your sales representative for details

**Glass** 5.7 lbs/linear in.

Polyethylene 6.5

Corrugated 2.50 lbs./in.

Painted Metal 7.0 lbs/linear in.

**Loop Tack** 5.00 oz/in<sup>2</sup>

# **Regulatory Approval**

RoHSProp65REACHYesYesYes

TPCH CPSIA Direct Food

Yes Yes No

#### **Indirect Food**

Yes

## Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

## Type

5517342

Tensile MD Tensile CD

34 22

Tear MD Tear CD 32 34

DescriptionValueBasis Weight40Caliper2.5

# **Regulatory Approval**

RoHSProp65REACHYesYesYes
TPCH
CPSIA
Yes
No

## **Direct Food**

No

Last update: 05/01/2024

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com