

ScandMet S SSP713 HG0

Description

ScandMet S is a bright silver metallised printing paper, that has been coated with a print receptive acrylic lacquer.

The material offers top print quality by all conventional print methods, like flexography, letterpress, offset and screen.

Note that special inks for non-absorbent materials should be used.

The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected. Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without notice.

Facestock

ScandMet S is a bright silver metallised printing paper, that has been coated with a print receptive acrylic lacquer. The material offers top print quality by all conventional print methods, like flexography, letterpress, offset and screen. Note that special inks for non-absorbent materials should be used.

Type

Paper

Properties

Method

Value

Basis Weight

ISO 536

74 ± 3g/m²

Caliper

ISO 534

73 ± 5µ

Smoothness

ISO 5627

> 12900s

Regulatory Approval

FSC

No

*Please contact your sales representative for details

Adhesive

SSP713 has excellent initial tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates. Particularly good adhesion to cardboard, plastic and glass. Note: Not advised for labelling highly plasticised materials, eg: flexible PVC

Type

Permanent

Composition

Rubber

Min. Application Temperature

8 F

Min. Service Temperature

-10 F

Max. Application Temperature

70 F

| Properties | Value | |
|---|---|------------------------------------|
| Stainless Steel | 18N | |
| Regulatory Approval | | |
| Direct Food | Indirect Food | Food contact |
| Yes | Yes | Complies with FDA175.105, BfR XIV. |
| FDA 21 CFR 175.105, BfR XIV | ISEGA approved for direct contact with dry and moist non-fatty foods | |
| Yes | Yes | |
| *Please contact your sales representative for details | | |

| Liner | | |
|---|----------|------------------------|
| HG0 honey glassine backing allows high speed conversion and consistent dispensing on a wide range of equipment. | | |
| Description | Method | Value |
| Basis Weight | ISO 536 | 55 ± 3g/m ² |
| Caliper | ISO 534 | 49 ± 3μ |
| Transparency | ISO 2469 | 50% |
| *Please contact your sales representative for details | | |

| Final product | |
|---|-----------|
| Description | Value |
| Typical Caliper | 142 ± 10μ |
| Format | |
| Roll | |
| Material Shelf Life | |
| 12 months stored at 20°C/50% RH | |
| *Please contact your sales representative for details | |

Last update: 05/01/2024

ADDRESS:

Beontag

Pål Anders väg 4, 263 35

Höganäs, Sweden

+46 42 25 00 50

orders.scandstick@beontag.com