

Pressure-sensitive adhesives

Acrylic

Paper

SOLAR YELLOW LABEL / TM-55 @ .8 CWT. / 40# SCK L-30

ITEM #78222

Facestock

A 50# yellow uncoated litho was designed with smudge resistance for high speed converting while still having excellent perforating, punching and fanfolding characteristics. This facestock is 30% PCW and will accept most standard ink methods including laser printing.

Type

Paper

Tensile MD

36 Lbs/in

Tensile CD

13 Lbs/in

Tear MD

40 Grams

Tear CD

46 Grams

Properties

Value

Basis Weight

50 # Rm 25 x 38

Caliper

4.10 Mil

Opacity

90

Regulatory Approval

FSC

No

*Please contact your sales representative for details

Adhesive

A specialty microsphere repositionable acrylic adhesive designed for roll to roll applications. This adhesive removes cleanly from most papers and a wide variety of substrates. Due to it's unique nature, TM55 cannot be coupled with any face/liner combination to achieve guaranteed lay flat properties.

Type

Removable

Composition

Acrylic

Shear

0

Min. Application Temperature

40 F

Min. Service Temperature

-10 F

Max. Application Temperature

150 F

Properties

Value

Stainless Steel

0.2 lbs/linear in.

Glass	0,3lbs/linear in.
Polyethylene	0
Corrugated	0.01 lbs./in.
Painted Metal	0.2 lbs/linear in.

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

17777

Tensile MD 34	Tensile CD 22
Tear MD 32	Tear CD 34

Description	Value
Basis Weight	40
Caliper	2.5

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

*Please contact your sales representative for details

Last update: 08/21/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com