



Pressure-sensitive adhesives

Acrylic

Paper

TECHNI-THERM DIRECT RX / TR440 @ 1.0 Cwt./ 40#SCK L-3

ITEM #68695

Facestock

An exceptional topcoated thermal label facestock specifically engineered for pharmacy prescription vial labels where superior image durability is required. The brightness of this Direct Thermal product is designed for dark images on pharmacy thermal printers.

Type

Paper

Tear MD

50 Grams

Tear CD

83 Grams

Properties

Value

Basis Weight

53

Caliper

3.20 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

Adhesive

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

Type

Removable

Composition

Acrylic

Shear

110

Min. Application Temperature

40 F

Min. Service Temperature

-65 F

Max. Application Temperature

150 F

Properties

Value

Stainless Steel

4.7 lbs/linear in.

Glass

3lbs/linear in.

Polyethylene	1.4
Corrugated	1.20 lbs./in.
Painted Metal	4.2 lbs/linear in.
Loop Tack	1.70 oz/in ²

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD 34	Tensile CD 22
Tear MD 32	Tear CD 34

Description	Value
Basis Weight	40
Caliper	2.5

Regulatory Approval

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com