

Pressure-sensitive adhesives

Acrylic

Acrylic

Paper

TECHNI-THERM DIRECT WS / TP170 @ 1.3 Cwt. / 40#SCK L-3

ITEM #899104

Facestock

A top coated direct thermal face with initial activation temperature of 185 F and an effective activation temperature of 280 F. Techni-Therm Direct WS has excellent light stability to resist fading from UV light and superior curl control to insure layflat properties.

Type

Paper

Tensile MD
20 Lbs/in
13 Lbs/in

Tear MD
40 Grams
50 Grams

Properties	Value
Basis Weight	53 # Rm 25 x 38
Caliper	3.20 Mil
Opacity	85
Brightness	89

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	FSC
Yes	Yes	No

^{*}Please contact your sales representative for details

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Type Permanent	Composition Acrylic	Shear 300
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 180 F

Properties	Value		
Stainless Steel	5.2 lbs/linear in.		
Glass	3,2lbs/linear in.		
Polyethylene	1.6		
Corrugated	1.40 lbs./in.		
Painted Metal	5.2 lbs/linear in.		
Loop Tack	2.20 oz/in ²		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	Direct Food	
Yes	Yes	No	

Adhesive

Indirect Food

Yes

Indirect Food

*Please contact your sales representative for details

Yes

A general purpose patterned acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Type Permanent Min. Application Temperature 35 F	Composition Acrylic Min. Service Temperature -65 F	Shear 0 Max. Application Temperature 180 F
Properties	Value	
Stainless Steel	5.2 lbs/linear in.	
Glass	3,2lbs/linear in.	
Polyethylene	1.6	
Painted Metal	5.2 lbs/linear in.	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	Direct Food
Yes	Yes	No

*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD Tensile CD

34 22

Tear MD Tear CD 32 34

Description	Value
Basis Weight	40
Caliper	2.5

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	UL
Yes	Yes	No

Prop65

Direct Food

No

Liner

RoHS

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Tensile MD 34	Tensile CD 22
Tear MD 32	Tear CD 34
Description	Value
Basis Weight	40
Caliper	2,5
Regulatory Approval	

REACH

^{*}Please contact your sales representative for details

	Yes	Yes	Yes	
	TPCH	CPSIA		
	Yes	Yes		
*Please contact your sales representative for details				

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com