



Pressure-sensitive adhesives    Acrylic    Acrylic    Paper

# TECHNI-THERM DIRECT WS / TP170 @ 1.3 Cwt. / 40#SCK L-3

ITEM #899104

## Facestock

A top coated direct thermal face with initial activation temperature of 185 F and an effective activation temperature of 280 F. Techni-Therm Direct WS has excellent light stability to resist fading from UV light and superior curl control to insure layflat properties.

### Type

Paper

### Tensile MD

20 Lbs/in

### Tensile CD

13 Lbs/in

### Tear MD

40 Grams

### Tear CD

50 Grams

Properties	Value
Basis Weight	53 # Rm 25 x 38
Caliper	3.20 Mil
Opacity	85
Brightness	89

## Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	FSC
Yes	Yes	No

\*Please contact your sales representative for details

## Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Type	Composition	Shear
Permanent	Acrylic	300
Min. Application Temperature	Min. Service Temperature	Max. Application Temperature
35 F	-65 F	180 F

Properties	Value	
Stainless Steel	5.2 lbs/linear in.	
Glass	3,2lbs/linear in.	
Polyethylene	1.6	
Corrugated	1.40 lbs./in.	
Painted Metal	5.2 lbs/linear in.	
Loop Tack	2.20 oz/in²	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	Direct Food
Yes	Yes	No
Indirect Food		
Yes		
*Please contact your sales representative for details		

Adhesive		
A general purpose patterned acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.		
Type	Composition	Shear
Permanent	Acrylic	0
Min. Application Temperature	Min. Service Temperature	Max. Application Temperature
35 F	-65 F	180 F
Properties	Value	
Stainless Steel	5.2 lbs/linear in.	
Glass	3,2lbs/linear in.	
Polyethylene	1.6	
Painted Metal	5.2 lbs/linear in.	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	Direct Food
Yes	Yes	No
Indirect Food		
Yes		

\*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34

Tensile CD

22

Tear MD

32

Tear CD

34

Description

Value

Basis Weight

40

Caliper

2.5

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

\*Please contact your sales representative for details

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Tensile MD

34

Tensile CD

22

Tear MD

32

Tear CD

34

Description

Value

Basis Weight

40

Caliper

2,5

Regulatory Approval

RoHS

Prop65

REACH

Yes	Yes	Yes
<b>TPCH</b>	<b>CPSIA</b>	
Yes	Yes	
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:  
Beontag  
6206 Wolf Creek Pike  
Trotwood, OH 45426  
[800-358-4448](tel:800-358-4448)  
[orders.us@beontag.com](mailto:orders.us@beontag.com)