



Pressure-sensitive adhesives

Latex

Latex

Paper

# TECHNI-THERM SP / AP151 @ 1.3 Cwt. / 40#SCK L-5

ITEM #73087

## Facestock

A coated one side thermal transfer facestock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This facestock also offers an 86% brightness and an 87% opacity.

### Type

Paper

### Tensile MD

26 Lbs/in

### Tensile CD

18 Lbs/in

### Tear MD

42 Grams

### Tear CD

42 Grams

### Properties

### Value

### Basis Weight

42 # Rm 24 x 26

### Caliper

2.70 Mil

### Opacity

87

### Brightness

86

## Regulatory Approval

### RoHS

Yes

### Prop65

Yes

### REACH

Yes

### TPCH

Yes

### CPSIA

Yes

### UL

No

### FSC

No

\*Please contact your sales representative for details

## Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

### Type

Permanent

### Composition

Latex

### Shear

80

### Min. Application Temperature

### Min. Service Temperature

### Max. Application Temperature

35 F

-65 F

220 F

**Properties****Value****Stainless Steel**

7.3 lbs/linear in.

**Glass**

5.7 lbs/linear in.

**Polyethylene**

6.5

**Corrugated**

2.50 lbs./in.

**Painted Metal**

7.0 lbs/linear in.

**Loop Tack**5.00 oz/in<sup>2</sup>**Regulatory Approval****RoHS**

Yes

**Prop65**

Yes

**REACH**

Yes

**TPCH**

Yes

**CPSIA**

Yes

**Direct Food**

No

**Indirect Food**

Yes

\*Please contact your sales representative for details

**Adhesive**

An outstanding general purpose permanent opaque adhesive that has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting and stripping traits. Provides opacity for cover up applications.

**Type**

Permanent

**Composition**

Latex

**Shear**

80

**Min. Application Temperature**

35 F

**Min. Service Temperature**

-65 F

**Max. Application Temperature**

220 F

**Properties****Value****Stainless Steel**

7.3 lbs/linear in.

**Glass**

5,7 lbs/linear in.

**Polyethylene**

6,5

**Corrugated**

2.50 lbs./in.

**Painted Metal**

7.0 lbs/linear in.

**Loop Tack**5.00 oz/in<sup>2</sup>**Regulatory Approval****RoHS**

Yes

**Prop65**

Yes

**REACH**

Yes

**TPCH****CPSIA****Direct Food**

Yes

Yes

No

**Indirect Food**

Yes

\*Please contact your sales representative for details

**Liner**

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

**Tensile MD**

34

**Tensile CD**

22

**Tear MD**

32

**Tear CD**

34

**Description**

**Value**

**Basis Weight**

40

**Caliper**

2,5

**Regulatory Approval**

**RoHS**

Yes

**Prop65**

Yes

**REACH**

Yes

**TPCH**

Yes

**CPSIA**

Yes

\*Please contact your sales representative for details

**Liner**

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

**Type**

5517353

**Tensile MD**

40

**Tensile CD**

24

**Tear MD**

44

**Tear CD**

48

**Description**

**Value**

**Basis Weight**

50

**Caliper**

3.2

**Regulatory Approval**

**RoHS**

Yes

**Prop65**

Yes

**REACH**

Yes

**TPCH**

Yes

**CPSIA**

Yes

**UL**

No

**Direct Food**

No

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

**ADDRESS:**

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)[orders.us@beontag.com](mailto:orders.us@beontag.com)