

Pressure-sensitive adhesives

Acrylic Acrylic

ic Paper

ULTRA WHITE SEMIGLOSS / TP170 @ 1.3 Cwt. / 40#SCK L-3

ITEM #86141

Facestock

A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 90% Brightness and an 88% opacity.

| Type Paper | | |
|--------------------------------|--------------------------------|-----------|
| Tensile MD 35 Lbs/in | Tensile CD 19 Lbs/in | |
| Tear MD 47 Grams | Tear CD 46 Grams | |
| Properties | Value | |
| Basis Weight | 60 # Rm 25 x 38 | |
| Caliper | 3.20 Mil | |
| Opacity | 88 | |
| Brightness | 90 | |
| Regulatory Approval | | |
| RoHS | Prop65 | REACH |
| Yes | Yes | Yes |
| TPCH Yes | CPSIA Yes | FSC No |

*Please contact your sales representative for details

Adhesive

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

| Type | Composition | Shear |
|-------------------------------------|---------------------------------|------------------------------|
| Permanent | Acrylic | 300 |
| Min. Application Temperature | Min. Service Temperature | Max. Application Temperature |
| 35 F | -65 F | 180 F |

| Properties | Value | |
|---|-------------------------|-------------|
| Stainless Steel | 5.2 lbs/linear in. | |
| | | |
| Glass | 3,2lbs/linear in. | |
| Polyethylene | 1.6 | |
| Corrugated | 1.40 lbs./in. | |
| Painted Metal | 5.2 lbs/linear in. | |
| Loop Tack | 2.20 oz/in ² | |
| Regulatory Approval | | |
| RoHS | Prop65 | REACH |
| Yes | Yes | Yes |
| ТРСН | CPSIA | Direct Food |
| Yes | Yes | No |
| Indirect Food | | |
| Yes | | |
| *Please contact your sales representative | for details | |

Adhesive

A general purpose patterned acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

| Type Permanent | Composition Acrylic | Shear 0 |
|---|--|--|
| Min. Application Temperature 35 F | Min. Service Temperature -65 F | Max. Application Temperature 180 F |
| Properties | We have | |
| Fioperties | Value | |
| Stainless Steel | 5.2 lbs/linear in. | |
| | | |

Painted Metal

5.2 lbs/linear in.

Regulatory Approval

| RoHS | Prop65 | REACH |
|------|--------|--------------------|
| Yes | Yes | Yes |
| | | |
| ТРСН | CPSIA | Direct Food |

Indirect Food Yes

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

| Type 5517342 | | | |
|----------------------------------|------------------------|-------|--|
| Tensile MD | Tensile CD | | |
| 34 | 22 | | |
| Tear MD | Tear CD | | |
| 32 | 34 | | |
| Description | Value | | |
| Basis Weight | 40 | | |
| Caliper | 2.5 | | |
| Regulatory Approval | | | |
| RoHS | Prop65 | REACH | |
| Yes | Yes | Yes | |
| ТРСН | CPSIA | UL | |
| Yes | Yes | No | |
| Direct Food | | | |
| No | | | |
| *Please contact your sales repre | esentative for details | | |

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 <u>800-358-4448</u> orders.us@beontag.com