



Pressure-sensitive adhesives

Latex

Paper

# 10 PT C1S TAG / TP120/LPG HCWT / 40#SCK L-30

ITEM #6097

## Facestock

A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers excellent stiffness and high internal strength.

### Type

Paper

### Tear MD

205 Grams

### Tensile CD

200 Grams

### Properties

### Value

### Caliper

10.00 Mil

## Regulatory Approval

### RoHS

Yes

### Prop65

Yes

### REACH

Yes

### TPCH

Yes

### CPSIA

Yes

### UL

No

### FSC

No

\*Please contact your sales representative for details

## Adhesive

A general purpose permanent rubber based adhesive showing high initial tack with high shear and high ultimate adhesion. It has fair plasticizer, UV and solvent resistance. TP120 is not recommended for water immersion. This adhesive has good adhesion to most substrates.

### Composition

Latex

### Type

Permanent

### Application Temperature

35 F

### Min. Application Temperature

-65 F

### Max. Application Temperature

200 F

## Typical Adhesion values

### Properties

### Value

### Stainless Steel

5.1 lbs/linear in.

### Glass

2.0

<b>Polyethylene</b>	5.0
<b>Painted Metal</b>	4.8 lbs/linear in.

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>Direct Food</b> No
<b>Indirect Food</b> Yes		

\*Please contact your sales representative for details

### Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

#### Type

17777

<b>Tensile MD</b> 34 Lbs/In	<b>Tensile CD</b> 22 Lbs/In
<b>Tear MD</b> 32 Grams	<b>Tensile CD</b> 34 Grams

Description	Value
<b>Basis Weight</b>	40 Lbs/Rm
<b>Caliper</b>	2.5 Mil

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		

\*Please contact your sales representative for details

Last update: 05/01/2024

**WARRANTY:** All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)