

Pressure-sensitive adhesives

Hot Melt

Film

# 1.6 MIL WHITE TC BOPP / TP750 @ 1.3 Cwt. / 50#SCK L-3

ITEM #92426

## Facestock

A white direct thermal topcoated, biaxially oriented (BOPP) film that may be used in a wide variety of pressure sensitive label applications. The solid white polypropylene core is treated one side with a print receptive gloss coating for superb ink adhesion, and has great stiffness for efficient dispensability.

### Type

Film

### Tensile MD

12000 Psi

### Tensile CD

32000 Psi

### Elong MD

145

### Elong CD

45

### Properties

### Value

### Caliper

1.60 Mil

### Opacity

89

## Regulatory Approval

### RoHS

Yes

### Prop65

Yes

### REACH

Yes

### TPCH

Yes

### CPSIA

Yes

### UL

No

### FSC

No

\*Please contact your sales representative for details

## Adhesive

A general purpose hotmelt adhesive with high initial tack and excellent ultimate adhesion. This adhesive demonstrates good resistance to water, UV, solvent and plasticizer. This adhesive has excellent die cutting characteristics for high speed, wide web processing. Excellent adhesion to corrugated and plastics.

### Composition

Hot Melt

### Type

Permanent

### Shear

60

### Application Temperature

25 F

### Min. Application Temperature

-65 F

### Max. Application Temperature

140 F

## Typical Adhesion values

Properties	Value
Stainless Steel	3.7 lbs/linear in.
Glass	2.0
Polyethylene	2.0
Painted Metal	4.5 lbs/linear in.
Loop Tack	2.50 lbs./in.

## Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>Direct Food</b> No
<b>Indirect Food</b> Yes		

\*Please contact your sales representative for details

## Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

### Type

5517353

### Tensile MD

40 Lbs/In

### Tensile CD

24 Lbs/In

### Tear MD

44 Grams

### Tensile CD

48 Grams

## Description

## Value

### Basis Weight

50 Lbs/Rm

### Caliper

3.2 Mil

## Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)