

Pressure-sensitive adhesives

Acrylic Film

2 MIL CLEAR ACETATE / TS523 @ 1.5 Cwt. / 1.2 MIL PET L-3

ITEM #84670

Facestock A 2 mil clear film with ex	cellent ink receptivity and printability.		
Type Film			
Tensile MD	Tensile CD		
10000 Psi	10000 Psi		
Elong MD			
325			
Properties	Value		
Caliper	2.00 Mil		
Regulatory Approva	ıl		
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	FSC	
Yes	Yes	No	
*Please contact your sales r	epresentative for details		

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Type Permanent	Composition Acrylic	Shear 300
Application Temperature 35 F	Min. Application Temperature -65 F	Max. Application Temperature 180 F
Properties	Value	
Properties Stainless Steel	Value 5.2 lbs/linear in.	

Polyethylene	2.9	
Corrugated	1.40 lbs./in.	
Painted Metal	5.2 lbs/linear in.	
Loop Tack	2.20 lbs./in2	
Regulatory Approval		
RoHS	Prop65	REACH
RoHS Yes	Prop65 No	REACH Yes
	-	
Yes	No	Yes
Yes TPCH	No CPSIA	Yes UL
Yes TPCH Yes	No CPSIA Yes	Yes UL

Liner

An economical 1.2 mil clear polyester film liner good for an array of prime label applications.

Tensile MD	Tensile CD		
30000	0		
Tear MD	Tear CD		
0	0		
Description	Value		
Basis Weight	0		
Caliper	1,2		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA		
Yes	Yes		

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448 orders.us@beontag.com