

Pressure-sensitive adhesives

Acrylic Film

## 2 MIL CLEAR POLYSTYRENE / AT333 @ 1.30 Cwt. / 44#PK L-4

ITEM #2174

## Facestock

A 2 mil optically clear polystyrene that is oriented, non-formable, non-UV stabilized printing and laminating grade film. This film complies with FDA direct food contact requirements.

<b>Type</b> Film <b>Tensile MD</b> 10800 Psi <b>Elong CD</b>	<b>Tensile CD</b> 10800 Psi	
100		
Properties	Value	
Caliper	2.00 Mil	
Regulatory Approval		
RoHS	Prop65	REACH
Yes	Yes	Yes
ТРСН	CPSIA	FSC
Yes	Yes	No
*Please contact your sales representative for details		

## Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

<b>Type</b> Permanent	<b>Composition</b> Acrylic	<b>Shear</b> 60
<b>Application Temperature</b> -20 F	<b>Min. Application Temperature</b> -65 F	Max. Application Temperature 160 F
Properties	Value	
Stainless Steel	4.7 lbs/linear in.	

Polyethylene	2.2		
Corrugated	1.40 lbs./in.		
Painted Metal	4.4 lbs/linear in.		
Loop Tack	2.20 lbs./in.		
Regulatory Approval			
RoHS	Prop65	REACH	

Yes	No	Yes	
ТРСН	CPSIA	UL	
Yes	Yes	No	
Direct Food	Indirect Food		
No	Yes		
*Places contact your color room			

\*Please contact your sales representative for details

## Liner

A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.

<b>Type</b> 17745			
Tensile MD	Tensile CD		
35 Lbs/In	13 Lbs/In		
Tear MD	Tear CD		
35 Grams	50 Grams		
Description	Value		
Basis Weight	44 Lbs/Rm		
Caliper	3.2 Mil		
Regulatory Approval			
RoHS	Prop65	REACH	
Yes	Yes	Yes	

<b>TPCH</b> Yes	<b>CPSIA</b> Yes
<b>Direct Food</b> No	
*Please contact your sales representative for c	letails

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

UL

No

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 <u>800-358-4448</u> <u>orders.us@beontag.com</u>