

2 MIL CLEAR POLYSTYRENE / TL250 @ 2.5 Cwt. / 40#SCK L-3

ITEM #9746

Facestock

A 2 mil optically clear polystyrene that is oriented, non-formable, non-UV stabilized printing and laminating grade film. This film complies with FDA direct food contact requirements.

Type

Film

Tensile MD

10800 Psi

Tensile CD

10800 Psi

Elong CD

100

Properties

Value

Caliper

2.00 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

<div><div>Adhesive</div><div>An outstanding general purpose permanent adhesive which has high initial tack and high ultimate adhesion. It is used for tire label and many other difficult to label substrates.</div></div>		
<div><div>Composition</div><div>Hot Melt</div></div>	<div><div>Type</div><div>Permanent</div></div>	<div><div>Shear</div><div>80</div></div>
<div><div>Application Temperature</div><div>35 F</div></div>	<div><div>Min. Application Temperature</div><div>-65 F</div></div>	<div><div>Max. Application Temperature</div><div>220 F</div></div>
<div><div>Properties</div><div>Value</div></div>		
<div><div>Stainless Steel</div></div>	<div><div>8.3 lbs/linear in.</div></div>	
<div><div>Glass</div></div>	<div><div>6.7</div></div>	

Polyethylene	7.5	
Corrugated	2.90 lbs./in.	
Painted Metal	8.0 lbs/linear in.	
Loop Tack	5.40 lbs./in2	
Regulatory Approval		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No	Indirect Food Yes	FDA 21 CFR 175.105, BfR XIV No
*Please contact your sales representative for details		

Liner Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type 5517342		
Tensile MD 34 Lbs/In	Tensile CD 22 Lbs/In	
Tear MD 32 Grams	Tear CD 34 Grams	
Description		
Value		
Basis Weight	40 Lbs/Rm	
Caliper	2.5 Mil	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com