



Pressure-sensitive adhesives Acrylic Film

2 MIL CLEAR POLYSTYRENE / TS523 @ 1.5 Cwt. / 44#PK L-4

ITEM #75771

Facestock

A 2 mil optically clear polystyrene that is oriented, non-formable, non-UV stabilized printing and laminating grade film. This film complies with FDA direct food contact requirements.

Type
Film

Tensile MD
10800 Psi

Tensile CD
10800 Psi

Elong CD
100

Properties	Value
Caliper	2.00 Mil

Regulatory Approval

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

FSC
No

*Please contact your sales representative for details

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Composition
Acrylic

Type
Permanent

Shear
300

Application Temperature
35 F

Min. Application Temperature
-65 F

Max. Application Temperature
180 F

Properties	Value
Stainless Steel	5.2 lbs/linear in.
Glass	2.8

Polyethylene	2.9	
Corrugated	1.40 lbs./in.	
Painted Metal	5.2 lbs/linear in.	
Loop Tack	2.20 lbs./in2	
Regulatory Approval		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No	Indirect Food Yes	
*Please contact your sales representative for details		

Liner A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.		
Type 17745		
Tensile MD 35 Lbs/In	Tensile CD 13 Lbs/In	
Tear MD 35 Grams	Tear CD 50 Grams	
Description Value		
Basis Weight	44 Lbs/Rm	
Caliper	3.2 Mil	
Regulatory Approval		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com