

2 MIL CRYSTAL CLEAR BOPP / IP400 @ 1.7 Cwt. / 44#PK L-4

ITEM #75831

<b>Facestock</b> A 2 mil clear biaxially oriented polypropylene with exceptional clarity, excellent die-cut performance and great stiffness. Coated gloss surface is print receptive for standard methods.		
<b>Type</b> Film		
<b>Tensile MD</b> 20,000 psi	<b>Tensile CD</b> 35,000 psi	
<b>Elong MD</b> 180	<b>Elong CD</b> 55%	
<b>Properties</b>	<b>Value</b>	
<b>Caliper</b>	2.00 Mil	
<b>Regulatory Approval</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>FSC</b> No		
*Please contact your sales representative for details		

<b>Adhesive</b> A specialty adhesive designed to adhere to glass wine bottles with good ultimate adhesion when applied at temperatures as low as +35 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for wet strength wine label facestocks when submersed in ice buckets.		
<b>Type</b> Permanent	<b>Composition</b> Acrylic	<b>Shear</b> 80
<b>Application Temperature</b> 35 F	<b>Min. Application Temperature</b> -65 F	<b>Max. Application Temperature</b> 200 F
<b>Properties</b>	<b>Value</b>	

Stainless Steel	5.5 lbs/linear in.	
Glass	3.2	
Polyethylene	2.0	
Corrugated	1.45 lbs./in.	
Painted Metal	3.0 lbs/linear in.	
Loop Tack	5.00 lbs./in.	
<hr/>		
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	
No	Yes	
<hr/>		
*Please contact your sales representative for details		

Liner

A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.

Type

17745

Tensile MD

35 Lbs/In

Tensile CD

13 Lbs/In

Tear MD

35 Grams

Tear CD

50 Grams

Description

Value

Basis Weight

44 Lbs/Rm

Caliper

3.2 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

\*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)