



Pressure-sensitive adhesives Acrylic Film

2 MIL CRYSTAL CLEAR BOPP / TR440 @ 1.0 Cwt. / 65# C2S L-3

ITEM #76780

Facestock

A 2 mil clear biaxially oriented polypropylene with exceptional clarity, excellent die-cut performance and great stiffness. Coated gloss surface is print receptive for standard methods.

Type
Film

Tensile MD
20,000 psi

Tensile CD
35,000 psi

Elong MD
180

Elong CD
55%

Properties

Value

Caliper

2.00 Mil

Regulatory Approval

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

UL
No

FSC
No

*Please contact your sales representative for details

Adhesive

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

Composition
Acrylic

Type
Removable

Shear
110

Application Temperature
40 F

Min. Application Temperature
-65 F

Max. Application Temperature
150 F

Properties

Value

Stainless Steel	4.7 lbs/linear in.
Glass	3.0
Polyethylene	1.4
Corrugated	1.20 lbs./in.
Painted Metal	4.2 lbs/linear in.
Loop Tack	1.70 lbs./in.

Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	
No	Yes	

*Please contact your sales representative for details

Liner

A fully bleached kraft liner which has been silicone coated one side to give a controlled release. This paper has high internal strength to withstand all conventional processing operations including, die-cutting, perforating, fanfolding and refolding processes.

<div>Tensile MD</div> <div>33</div>	<div>Tensile CD</div> <div>18</div>
<div>Tear MD</div> <div>51</div>	<div>Tear CD</div> <div>51</div>

Description	Value
Basis Weight	0
Caliper	3,8

Regulatory Approval

<div>RoHS</div> <div>Yes</div>	<div>Prop65</div> <div>Yes</div>	<div>REACH</div> <div>Yes</div>
<div>TPCH</div> <div>Yes</div>	<div>CPSIA</div> <div>Yes</div>	

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages. BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at

BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com