

# 2 MIL CRYSTAL CLEAR BOPP / TS523 HCWT / 4.6 MIL LAYFLAT L-3

ITEM #75779

## Facestock

A 2 mil clear biaxially oriented polypropylene with exceptional clarity, excellent die-cut performance and great stiffness. Coated gloss surface is print receptive for standard methods.

Type  
Film

Tensile MD  
20,000 psi

Tensile CD  
35,000 psi

Elong MD  
180

Elong CD  
55%

Properties	Value
------------	-------

Caliper	2.00 Mil
---------	----------

## Regulatory Approval

RoHS	Yes	Prop65	Yes	REACH	Yes
TPCH	Yes	CPSIA	Yes	UL	No
FSC	No				

\*Please contact your sales representative for details

## Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Composition	Type	Shear
Acrylic	Permanent	350
Application Temperature	Min. Application Temperature	Max. Application Temperature
35 F	-65 F	180 F

Properties	Value
------------	-------

Stainless Steel	5.2 lbs/linear in.	
Glass	2.8	
Polyethylene	2.9	
Corrugated	1.40 lbs./in.	
Painted Metal	5.2 lbs/linear in.	
Loop Tack	2.20 lbs./in2	
<hr/>		
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	
No	Yes	
*Please contact your sales representative for details		

Liner

A clay coated kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand all diecutting, margin punching, perforating, fanfolding and refolding processes. It is an excellent layflat liner.

Type

719363

Tensile MD

51 Lbs/In

Tensile CD

0 Lbs/In

Tear MD

Grams

Tear CD

100 Grams

Description

Value

Basis Weight

72 Lbs/Rm

Caliper

4.6 Mil

Regulatory Approval

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

\*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)