

Pressure-sensitive adhesives

Acrylic

Film

2 MIL GLOSS WHITE TC POLYESTER / AT333 @ 1.30 Cwt. / 50#SCK L-3

ITEM #8571

Facestock

A 2 mil white TC polyester with a smooth gloss finish. This film has excellent durability and resistance to harsh weather and environments including extreme temperatures, chemicals, moisture, solvents and UV light. Compatible with water-based flexo, UV flexo and thermal transfer print methods.

Туре

Film

Tensile MD28000 Psi

Tensile CD
34000 Psi

Tear MD 1500 Grams

Elong MD300
Elong CD
110

Properties Value

Caliper 2.00 Mil

Regulatory Approval

RoHSProp65REACHYesYesYes
TPCH
CPSIA
FSC
Yes
No

*Please contact your sales representative for details

Adhesive

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Type Permanent	Composition Acrylic	Shear 60
Application Temperature -20 F	Min. Application Temperature -65 F	Max. Application Temperature 160 F
Properties	Value	

Stainless Steel 4.7 lbs/linear in.

Glass 1.3

Polyethylene 2.2

Corrugated 1.40 lbs./in.

Painted Metal 4.4 lbs/linear in.

Loop Tack 2.20 lbs./in.

Regulatory Approval

RoHSProp65REACHYesNoYesTPCHCPSIAUL

Yes

Direct Food Indirect Food

No Yes

Liner

Yes

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

No

Type

5517353

Tensile MDTensile CD40 Lbs/In24 Lbs/In

Tear MD44 Grams
48 Grams

Description Value

Basis Weight 50 Lbs/Rm

Caliper 3.2 Mil

Regulatory Approval

RoHSProp65REACHYesYesYes
TPCH
Yes
CPSIA
Yes
No

Direct Food

No

Last update: 05/01/2024

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com