

Pressure-sensitive adhesives

Acrylic

Film

# 2 MIL MATTE CLEAR POLYESTER / TS523 @ 1.5 Cwt. / 50#SCK L-3

ITEM #4625

#### **Facestock**

A 2 mil clear top-coated polyester with a very smooth matte finish. It has excellent tear strength, heat resistance and dimensional stability thermal transfer and most standard ink receptivity.

## Туре

Film

**Tensile MD**28000 Psi
Tensile CD
34000 Psi

**Tear MD** 1400 Grams

**Elong MD**300
Elong CD

Properties Value

Caliper 2.00 Mil

### **Regulatory Approval**

RoHS<br/>YesProp65<br/>YesREACH<br/>YesTPCH<br/>YesCPSIA<br/>YesFSC<br/>No

#### **Adhesive**

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

CompositionTypeShearAcrylicPermanent300Application TemperatureMin. Application TemperatureMax. Application Temperature35 F-65 F180 F

Properties Value

<sup>\*</sup>Please contact your sales representative for details

**Stainless Steel** 5.2 lbs/linear in.

Glass 2.8

Polyethylene 2.9

Corrugated 1.40 lbs./in.

Painted Metal 5.2 lbs/linear in.

**Loop Tack** 2.20 lbs./in2

## **Regulatory Approval**

RoHSProp65REACHYesNoYesTPCHCPSIAUL

Yes

Direct Food Indirect Food

No Yes

#### Liner

Yes

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

No

# Туре

5517353

44 Grams

Caliper

Tensile MD
40 Lbs/ln
24 Lbs/ln
Tear MD
Tear CD

Description Value

Basis Weight 50 Lbs/Rm

## **Regulatory Approval**

RoHS<br/>YesProp65<br/>YesREACH<br/>YesTPCH<br/>YesCPSIA<br/>YesUL<br/>No

3.2 Mil

48 Grams

#### **Direct Food**

No

Last update: 05/01/2024

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS: Beontag 222 Mound Avenue Miamisburg, OH 45342

800-358-4448 orders.us@beontag.com