



Pressure-sensitive adhesives

Hot Melt

Film

# 2 MIL MATTE SILVER CP POLYESTER / TR447 @ 1.4 Cwt. / 40#SCK L-3

ITEM #85187

## Facestock

A 2 mil silver top-coated polyester with a very smooth matte finish. It has excellent tear strength, heat resistance and dimensional stability, while the CP top-coating allows for laser, thermal transfer and most standard ink receptivity.

Type  
Film

Tensile MD  
28000 Psi

Tensile CD  
34000 Psi

Tear MD  
1400 Grams

Elong MD  
300

Elong CD  
110

Properties

Value

Caliper

2.00 Mil

## Regulatory Approval

RoHS  
Yes

Prop65  
Yes

REACH  
Yes

TPCH  
Yes

CPSIA  
Yes

FSC  
No

\*Please contact your sales representative for details

## Adhesive

A general purpose, removable rubber based emulsion adhesive featuring good initial tack and moderate adhesion. It has limited plasticizer, UV and solvent resistance. This is a standard removable adhesive for tape reels, computer disks and kids stickers.

Composition  
Hot Melt

Type  
Removable

Shear  
40

Application Temperature  
40 F

Min. Application Temperature  
1 F

Max. Application Temperature  
120 F

Properties

Value

Stainless Steel	2.5 lbs/linear in.	
Glass	0.9	
Polyethylene	1.8	
Corrugated	1.00 lbs./in.	
Painted Metal	1.6 lbs/linear in.	
Loop Tack	1.50 lbs./in.	
<hr/>		
Regulatory Approval		
RoHS	Prop65	REACH
Yes	No	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food	Indirect Food	
No	Yes	
*Please contact your sales representative for details		

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34 Lbs/In

Tensile CD

22 Lbs/In

Tear MD

32 Grams

Tear CD

34 Grams

Description

Value

Basis Weight

40 Lbs/Rm

Caliper

2.5 Mil

Regulatory Approval

RoHS

Yes

TPCH

Yes

Direct Food

No

Prop65

Yes

CPSIA

Yes

REACH

Yes

UL

No

\*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

222 Mound Avenue Miamisburg, OH 45342

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)