

Pressure-sensitive adhesives

Acrylic

Film

# 2 MIL MATTE SILVER CP POLYESTER / TS523 @ 1.5 Cwt. / 3.4 MIL LAYFLAT L-3

ITEM #84633

#### **Facestock**

A 2 mil silver top-coated polyester with a very smooth matte finish. It has excellent tear strength, heat resistance and dimensional stability, while the CP top-coating allows for laser, thermal transfer and most standard ink receptivity.

#### **Type**

Film

**Tensile MD**28000 Psi

Tensile CD
34000 Psi

**Tear MD** 1400 Grams

**Elong MD**300
Elong CD

Properties Value

Caliper 2.00 Mil

### **Regulatory Approval**

RoHS<br/>YesProp65<br/>YesREACH<br/>YesTPCH<br/>YesCPSIA<br/>YesFSC<br/>No

#### **Adhesive**

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

<b>Type</b> Permanent	<b>Composition</b> Acrylic	Shear 300
<b>Application Temperature</b> 35 F	<b>Min. Application Temperature</b> -65 F	<b>Max. Application Temperature</b> 180 F
Properties	Value	

<sup>\*</sup>Please contact your sales representative for details

Stainless Steel	5.2 lbs/linear in.

Glass 2.8

Polyethylene 2.9

Corrugated 1.40 lbs./in.

Painted Metal 5.2 lbs/linear in.

**Loop Tack** 2.20 lbs./in2

#### **Regulatory Approval**

RoHS<br/>YesProp65<br/>NoREACH<br/>YesTPCHCPSIAUL

Yes

Direct Food Indirect Food

No Yes

#### Liner

35

Yes

A bleached kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand die-cutting, marginal punching, perforating, fanfolding and refolding process while providing excellent dimensional stability.

No

Tensile MD	Tensile CD	

15

**Tear MD**50 **Tear CD**75

Description	Value
Basis Weight	0
Caliper	3,4

## **Regulatory Approval**

RoHS	Prop65	REACH
Yes	Yes	Yes

TPCH
Yes

CPSIA
Yes

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at

<sup>\*</sup>Please contact your sales representative for details

<sup>\*</sup>Please contact your sales representative for details

BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com