

Pressure-sensitive adhesives

Acrylic

Film

2 MIL MATTE SILVER CP POLYESTER / TS523 @ 1.5 Cwt. / 50#SCK L-3

ITEM #4631

Facestock

A 2 mil silver top-coated polyester with a very smooth matte finish. It has excellent tear strength, heat resistance and dimensional stability, while the CP top-coating allows for laser, thermal transfer and most standard ink receptivity.

Туре

Film

Tensile MD28000 Psi

Tensile CD
34000 Psi

Tear MD 1400 Grams

Elong MD300
Elong CD

Properties Value

Caliper 2.00 Mil

Regulatory Approval

RoHS
YesProp65
YesREACH
YesTPCH
YesCPSIA
YesFSC
No

Adhesive

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

CompositionTypeShearAcrylicPermanent350

Application Temperature Min. Application Temperature Max. Application Temperature

35 F -65 F 200 F

Typical Adhesion values

Properties Value

^{*}Please contact your sales representative for details

Stainless Steel	5.6 lbs/linear in.
Stalliless Steel	5.0 IDS/III lear III.

Glass 2.0

Polyethylene 2.0

Corrugated 1.50 lbs./in.

Painted Metal 4.9 lbs/linear in.

Loop Tack 2.70 lbs./in.

Regulatory Approval

RoHS	Prop65	REACH
Yes	Yes	Yes

TPCH CPSIA Direct Food

Yes Yes No

Indirect Food

Yes

Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Туре

5517353

Tensile MDTensile CD40 Lbs/In24 Lbs/In

Tear MD44 Grams
48 Grams

Description Value

Basis Weight 50 Lbs/Rm

Caliper 3.2 Mil

Regulatory Approval

RoHSProp65REACHYesYesYes
TPCH
CPSIA
Yes
No

Direct Food

No

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
222 Mound Avenue Miamisburg, OH 45342
800-358-4448
orders.us@beontag.com